



H-2072 Zsámbék, Új Gyártelep, Tel: +36/23-342-238, Fax: +36/23-342-286
E-mail: qualchem@qualchemrt.hu, Website: www.qualchemrt.hu

TECHNICAL DATA SHEET

BIOMID 66 GF30

PROPERTY	UNITS	METHOD	TYPICAL VALUES (Dry)
Density	G/cm ³	ASTM D 792	1,34
H ₂ O absorption	%	ASTM D 570	0,7~1,0
Mold. shrinkage	%		0,4~0,5
Rockwell	R scale	ASTM D 785	115~118
Elastic Def. Mod.	N/mm ²	ASTM D 790	7500~8000
Elong. at break	%	ASTM D 638	3,0~3,5
Notched izod	J/m	ASTM D 256	80~90
Melting point	°C	ASTM D 2117	258
H.D.T. 1.80 MPA	°C	ASTM D 648	235

The supplied data are to our best knowledge but they are only indicative average values of the mentioned product. Above values do not bind Bio Polymer s.r.l. to any loss or damage sustained by the end user.